

THOMSON
DELPHION™

RESEARCH

PRODUCTS

INSIDE DELPHION

[Inpadoc](#) | [News](#) | [Patent](#) | [My Account](#) | [Products](#)Search: [Quick/Number](#) [Boolean](#) [Advanced](#) [Derwent](#)

The Delphion Integrated View

Get Now: ☒ PDF | [More choices...](#)Tools: Add to Work File: [Create new Work File](#) ☐View: [INPADOC](#) | Jump to: [Top](#) ☐ Go to: [Derwent](#)☒ Email this to a

🔍 Title: **JP7094189A2: WATERPROOFING METHOD FOR CARBON ROD FOR DRY BATTERY**

🔍 Derwent Title: Carbon waterproofing process for dry batteries - comprises immersing carbon into warm paraffin wax heated to specific temp. and gradually increasing temp. of wax [\[Derwent Record\]](#)

🔍 Country: **JP Japan**
🔍 Kind: **A** (See also: [JP2770716B2](#))

🔍 Inventor: **UNO MASATOSHI;**
MAEDA MASANORI;

🔍 Assignee: **MATSUSHITA ELECTRIC IND CO LTD**
[News, Profiles, Stocks and More about this company](#)

🔍 Published / Filed: **1995-04-07 / 1993-09-21**

🔍 Application Number: **JP1993000234509**

🔍 IPC Code: **H01M 4/64; H01M 4/75; H01M 6/08;**

🔍 Priority Number: **1993-09-21 JP1993000234509**

🔍 Abstract: **PURPOSE:** To provide a waterproofing method which is easy to handle and safety by immersing a carbon rod for a dry battery in oil which is heated and kept at a specified temperature for a specified time, then by heating at a temperature same as or higher than the temperature of the oil.


CONSTITUTION: A carbon rod for a dry battery, which is baked but not yet waterproof treated is immersed in oil or paraffin wax heated and kept at 80-150°C for 3-10 minutes, then taken out. The carbon rod is heated at a temperature higher than the temperature of the oil or paraffin wax for several hours. The carbon rod having high air permeability and satisfying the blind core test can be obtained.


COPYRIGHT: (C)1995,JPO

🔍 INPADOC Legal Status: **None** **Get Now:** [Family Legal Status Report](#)

🔍 Family: [Show 2 known family members](#)

🔍 Forward References: **Go to Result Set: Forward references (1)**

PDF	Patent	Pub.Date	Inventor	Assignee	Title
	US6586912	2003-07-01	Tsukamoto; Hisashi	Quallion LLC	Method and apparatus for amplitude limiting battery temperature spikes

**Best Available Copy**

Other Abstract
Info:

DERABS C95-173464 DERC95-173464



[Nominate this for the Gallery...](#)



© 1997-2004 Thomson

[Research Subscriptions](#) | [Privacy Policy](#) | [Terms & Conditions](#) | [Site Map](#) | [Contact Us](#) | [Help](#)



(19)

(11) Publication number: **07094**

Generated Document.

PATENT ABSTRACTS OF JAPAN(21) Application number: **05234509**(51) Intl. Cl.: **H01M 4/64** H01M 4/75 H01M 6/08(22) Application date: **21.09.93**

(30) Priority:

(43) Date of application
publication: **07.04.95**(84) Designated contracting
states:(71) Applicant: **MATSUSHITA ELECTRIC IN:
LTD**(72) Inventor: **UNO MASATOSHI
MAEDA MASANORI**

(74) Representative:

**(54) WATERPROOFING
METHOD FOR CARBON ROD
FOR DRY BATTERY**

(57) Abstract:

PURPOSE: To provide a waterproofing method which is easy to handle and safety by immersing a carbon rod for a dry battery in oil which is heated and kept at a specified temperature for a specified time, then by heating at a temperature same as or higher than the temperature of the oil.

CONSTITUTION: A carbon rod for a dry battery, which is baked but not yet waterproof treated is immersed in oil or paraffin wax heated and kept at 80-150°C for 3-10 minutes, then taken out. The carbon rod is heated at a temperature higher than the temperature of the oil or paraffin wax for several hours. The carbon rod having high air permeability and satisfying the blind core test can be obtained.

COPYRIGHT: (C)1995,JPO